

Testreihe sulfatierte Akkus 2013

<u>Messung</u>	<u>Akku 1</u> <u>Klemmenspannung (12 V)</u>	<u>Elektrolytdichte</u>						<u>Mittelwert</u>	<u>Sulfatierung</u> in Prozent
		Zelle 1	Zelle 2	Zelle 3	Zelle 4	Zelle 5	Zelle 6		
09.11.2013	6,81 V							1,1	64,29%
23.11.2013									
26.11.2013	12,38 V	1,23	1,20	1,20	1,23	1,23	1,15	1,21	26,19%
27.11.2013									
28.11.2013		1,24	1,23	1,23	1,24	1,23	1,20	1,23	18,45%
29.11.2013									
30.11.2013	12,61 V	1,24	1,23	1,24	1,25	1,23	1,18	1,23	18,45%
	V								
	V								
	V								
	V								
	V								
	V								
	V								
	V								
	V								
	V								
	V								
<u>Zielvorgabe:</u>	12,7 V							1,28	0,00%

Testreihe sulfatierte Akkus 2013

[illegible]

Testreihe sulfatierte Akkus 2013

<u>Messung</u>	<u>Akku 3</u>		<u>Elektrolytdichte</u>						<u>Mittelwert</u>		<u>Sulfatierung</u> in Prozent
	<u>Klemmenspannung (12 V)</u>		Zelle 1	Zelle 2	Zelle 3	Zelle 4	Zelle 5	Zelle 6			
09.11.2013											
23.11.2013	12,42 V								1,20		28,57%
26.11.2013	12,66 V		1,26	1,17	1,25	1,20	1,23	1,24	1,23		19,64%
27.11.2013											
28.11.2013			1,26	1,24	1,25	1,23	1,23	1,27	1,25		11,90%
29.11.2013											
30.11.2013	12,68 V		1,27	1,24	1,25	1,21	1,25	1,26	1,25		11,90%
01.12.2013	V										
02.12.2013	V										
	V										
	V										
	V										
	V										
	V										
	V										
	V										
	V										
	V										
	V										
	V										
	V										
<u>Zielvorgabe:</u>	12,70 V								1,28		0,00%